

Metal Alloys Corporation





C62300 aluminum bronze applications include valve and pump components for industrial process streams, as well as for marine equipment, high strength fasteners and pole line hardware.

TYPICAL USES:

FASTENERS: Nuts, Bolts **INDUSTRIAL:** Gears, Bearing Races, Valve Stems, Worm Gears, Valve Guides, Valve Seats, Bearings, Bushings, Cams, Pump Rods **MARINE:** Marine Hardware

CHEMICAL COMPOSITION

	Al	Cu	Fe	Mn	Ni	Si	Sn
Min/Max	8.5 - 10.0	Rem	2.0 - 4.0	0.5	1	0.25	0.6
Nominals	10.0000	87.0000	3.0000	-	-	-	-

PHYSICAL PROPERTIES

Product Property	US Customary			
Coefficient of Thermal Expansion	9.0 Â • 10-6 per oF (68-572 F)			
Density	0.277 lb/in3 @ 68 F			
Electrical Conductivity	12 %IACS @ 68 F			
Electrical Resistivity	86.4 ohms-cmil/ft @ 68 F			
Melting Point Liquid US	1915 F			
Melting Point Solid US	1905 F			
Modulas of Elasticity in Tension	17000 ksi			
Modulas of Rigidity	6400 ksi			
Specific Gravity	7.67			
Specific Heat Capacity	0.09 Btu/lb/°F @ 68 F			
Thermal Conductivity	31.0 Btu • ft/(hr • ft2 •°F) @ 68 F			

SIZES AVAILABLE:

ROUND RODS 8mm To 100 mm
HEX 10mm To 60mm
SQUARE 10mm To 60mm

FLAT 10mm Min Thickness and max Width 120mm

BILLETS Up to 200 mm
INGOTS As per Specification

Regd. Office & Plant

Plot No. 6 & 7, Village: Lakhabaval, Post: Khodiyar Colony, Jamnagar - 361006. Tel.: +91-288-2889251 / 52, Fax: +91-288-2889223, Cell: +91-9924443396 Email: info@metalalloyscorp.com • web: www.metalalloyscorp.com





